

### ABSTRACT OF THE DISCLOSURE

Lubricating oil compositions for internal combustion engines ~~comprises~~include a mineral and/or synthetic base oil, (A) a succinimide-based ashless dispersant in an amount of 0.08 to 0.40 percent by mass in terms of nitrogen, (B) a metallic detergent in an amount of 0.06 to 0.22 percent by mass in terms of metal element, (C) a zinc secondary alkyldithiophosphate in an amount of 0.04 to 0.08 percent by mass in terms of phosphorus, and (D) a phosphorus-containing ashless anti-wear agent in an amount of 0.01 to 0.04 percent by mass in terms of phosphorus and contains sulfated ashes derived from the metal elements in the composition in an amount of 0.3 to 1.0 percent by mass. The lubricating oil compositions are excellent in anti-wear properties and high-temperature detergency although they are decreased in ash content.

Document comparison done by DeltaView on Monday, March 15, 2004 3:29:52 PM

Input:	
Document 1	PowerDocs://EAST/7150945/1
Document 2	PowerDocs://EAST/7159867/1
Rendering set	Patent

Legend:	
Insertion	
Deletion	
Moved from	
Moved to	
Style change	
Format change	
Moved deletion	
Inserted cell	
Deleted cell	
Moved cell	
Split/Merged cell	
Padding cell	

Statistics:	
	Count
Insertions	30
Deletions	26
Moved from	0
Moved to	0
Style change	0
Format changed	0
Total changes	56